

KIM.

This powder is to be added to the mix that forms your hearth. There is a sufficient amount in each punnet sold from PIAZZA, to mix with one 40kg bag of cement. If your concrete mixer is capable of holding about quarter of a bag of cement then use a quarter of this container in the brew. Put KIM into the mix when you put the cement in. Let the mixer turn for 10 minutes to ensure KIM is evenly dispersed into your mix. The mix should be 4 gravel; to 1 cement. If using coarse sand make it 3sand; to 1 cement.

It takes 3-4 concrete mixer loads to do an average hearth. It is important the last brew you put on top of your hearth has a good ratio of KIM additive. So don't use up all the KIM on your first brews. The top one is the most important. This will keep rain water from soaking into your hearth and improve your cooking no end.

Wear a dust mask when handling cement and KIM. Wash hands with warm soapy water. Keep KIM out of the reach of children.

Happy Cooking!

**A dry hearth means a happy oven...
Always use KIM. in your hearth pour.**

